




TM

MOLYKOTE®

FROM DOW CORNING

Bearing Greases



AV05840


A complete line of trusted industrial lubrication solutions.

Molykote® Product Selection Guide

To determine which grease is right for your application, start at the left of the selection guide, and follow your criteria until you reach a Molykote bearing grease. If you have multiple criteria (i.e., low temp and food grade), select the most important criteria and continue until you reach the Molykote grease designed for your application.


Multipurpose:

- G-4500 Food Grade
- G-4700 PAO
- G-0101 No solid lubricants
- BR2-plus Solid lubricants



Molykote® Bearing Grease Product Specifications

Name	Description	Color	Temperature Range	Thickener/Base oil	Base oil viscosity mm ² /s at 40°C/104°F
41	Heavy duty silicone	Black	-18°C/0°F to +288°C/+550°F	Carbon black/Silicone	138
FS-3451	Chemical resistant silicone	White	-40°C/-40°F to +230°C/+446°F	PTFE/Fluoro-Silicone	491
33 light	Low temperature silicone, light consistency	Pink	-73°C/-100°F to +180°C/+356°F	Lithium soap/Silicone	79
33 medium	Low temperature silicone, medium consistency	Pink	-73°C/-100°F to +180°C/+356°F	Lithium soap/Silicone	79
44 light	High temperature silicone, light consistency	Brown	-40°C/-40°F to +200°C/+392°F	Lithium soap/Silicone	70
44 medium	High temperature silicone, medium consistency	Brown	-40°C/-40°F to +200°C/+392°F	Lithium soap/Silicone	70
BG 20	High performace synthetic	Beige	-45°C/-49°F to +180°C/+356°F	Lithium complex/Ester	55
BG 555	Low noise synthetic	Light straw	-40°C/-40°F to +150°C/+302°F	Lithium soap/Ester	26
BR2-plus	Multipurpose solid lubricants	Black	-30°C/-22°F to +130°C/+266°F	Lithium soap/Mineral	114
G-0100	High performance polyurea	Yellowish beige	-40°C/-40°F to +170°C/+338°F	Polyurea/Mineral	96
G-0101	Multipurpose	Yellowish brown	-20°C/-4°F to +150°C/+302°F	Lithium Complex/ Mineral	101
G-0102	Heavy duty	Brown	-25°C/-13°F to +140°C/+284°F	Calcium Complex/ Mineral	150
G-1001	Low noise semi-synthetic	Light brown	-30°C/-22°F to +150°C/+302°F	Lithium Complex/ Mineral PAO Blend	58
G-2001	High speed	Beige	-50°C/-58°F to +130°C/+266°F	Lithium Calcium Soap/PAO	35
G-4500	Multipurpose synthetic foodgrade	White	-51°C/-60°F to +163°C/+325°F	Aluminum Complex/ PAO	110
G-4700	Multipurpose synthetic solid lubricants	Black	-40°C/-40°F to +177°C/+350°F	Lithium Complex/PAO	150
G-6000	Chemical resistant synthetic	Light brown	-40°C/-40°F to +200°C/+392°F	Polyurea/Phenylether	103
HP 300	Extreme temperature foodgrade	White	-35°C/-31°F to +250°C/+482°F	Fluorinated polymer/ Perfluoro polyether	160
HP 870	Extreme temperature	White	-20°C/-4°F to +250°C/+482°F	Fluorinated polymer/ Perfluoro polyether	350
Longterm 2 plus	High viscosity solid lubricants	Black	-25°C/-13°F to +110°C/+230°F	Lithium soap/Mineral	265
White Bearing Grease	Foodgrade	White	-17°C/+1°F to +149°C/+300°F	Aluminum Complex/ Mineral	92



How To Contact Us

For nearly 60 years, OEM designers, maintenance and materials engineers around the world have trusted the Molykote® brand for performance and expertise to solve or prevent lubrication problems. Molykote solutions are available through a distributor network of more than 3,000 channel partners around the globe. To learn more about our extensive product and service offering, visit www.molykote.com or email industrial@dowcorning.com.

LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended use. Suggestions of uses should not be taken as inducements to infringe any particular patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Molykote is a registered trademark of Dow Corning Corporation.

Dow Corning is a registered trademark of Dow Corning Corporation.

© 2004 Dow Corning Corporation. All rights reserved.

Form No: 80-3222-01

Design: APCO Worldwide

DOW CORNING